

Declaration of conformity

on plastic materials and articles intended to come into contact with food

We declare under our sole responsibility that our products:

Measuring scoops 100 ml, PP, yellow

item no. 396946

meet the present requirements of the Ordinance on Materials and Articles and Regulation (EC) No 1935/2004^[1] and Commission Regulation (EU) Nr.10/2011^[2] in their actual version (inclusive of their amendments), too.

Analyses by an independent, accredited laboratory according to the overall migration limit of the final article validates no overstepping of the regulated limits. Also, during the organoleptic tests no negative interaction with the food (change of taste and odour of the food) could be discovered. The testing has been performed according to article 17 and 18 of Commission Regulation (EU) No 10/2011 in conjunction with Annex V. Therefore, the above-named products comply with the requirements of Commission Regulation (EU) No. 10/2011 and could be used related to the specified limitation of migration limits in contact with food.

According to statements provided by our raw materials supplier we could declare, that the material currently used for production of the above-named products, has been manufactured in accordance with the relevant requirements of good manufacturing practice for articles intended to come into contact with food, according to Commission Regulation (EC) No 2023/2006^[3].

Unless the raw material used for the production of the above-named products contains substances with specified limitation (SML / QM) the defined limiting values according to Commission Regulation (EU) No 10/2011 were observed. The actual version of the Commission Regulation can be downloaded from the Internet at <http://eur-lex.europa.eu> or <http://bfr.bund.de>.

^[1] OJ L 338, 13.11.2004, p. 4–17

^[2] OJ L 12, 15.1.2011, p. 1–89

^[3] OJ L 384, 29.12.2006, p. 75–78

1. Specification for envisaged use or limitations:

- Kind of food, which could come into contact with the used material:

All types of food (dry, aqueous, sour, alcoholic, fatty) - tested according to table 3 annex III with listed food simulants (1. distilled water or water of equivalent quality or food simulant A (Ethanol 10 Vol.-%); 2. food simulant B (Acetic acid 3 Gew.-%); and 3. food simulant D2 (Any vegetable oil with less than 1 % unsaponifiable matter) - with 95% ethanol and isooctane alternatively according to annex V, chapter 2 paragraph 2.1.3 Conditions of contact when using food simulants.).

- Kind of food, which should not come into contact with the used material:

- (non)

2. Information on the intended field of application:

- Contact time and contact temperature for using and storing food:

tested according to table 3 annex IV for all kind of food, for 10 days at 40 °C (Isooctane for 2 days at 20 °C) resp. for 10 days at 60 °C - shall cover all storage times at refrigerated and frozen conditions including hot-fill conditions and/or heating up to a temperature T, between 70 °C ≤ T ≤ 100 °C, for a period of no more than $t = 120/2^{((T-70)/10)}$ minutes.

3. Research results:

3.1. Organoleptic test (triangle test, 6 persons) according DIN EN 10955:2004-06

Test conditions:

Type of contact: *Insert*

Used simulant: *Mineral water after 10 d at 40 °C*

	Intensity	Significance	Limiting value ^[4]	Assessment
Deterioration of smell	0	> 20 %	max. 2.5	<i>passed</i>
Deterioration of taste	0	> 20 %	max. 2.5	<i>passed</i>

Scale of intensity: 0 = imperceptible
1 = just discernible
2 = discernible
3 = clear
4 = strong

3.2. Colour fastness (BfR-Recommendation IX 2010-01)

Colourfast against...	dist. water	acetic acid 2 %	ethanol 10 %	peanut oil
Result for sample	<i>„colourfast“</i>	<i>„colourfast“</i>	<i>„colourfast“</i>	<i>„colourfast“</i>

3.3. Overall migration

Test conditions:

Type of contact: *Insert*

Method: *DIN EN 1186:2002-07*

Migration with the following used simulants:

Acetic Acid 3 % for 10 d at 40 °C, with a S:V of 3.8 dm²:500 ml

Ethanol 10 % for 10 d at 40 °C, with a S:V of 3.8 dm²:500 ml

Olive oil for 10 d at 40 °C, with a S:V of 1.0 dm²:165 ml

Ethanol 95 % for 10 d at 40 °C, with a S:V of 3.8 dm²:500 ml

Isooctane for 2 d at 20 °C, with a S:V of 3.8 dm²:500 ml

permitted limit value: max. 10.0 mg/dm² [5].

Food-simulant	Unit	Measutrement uncertainty	Sample	1. Contact	2. Contact	3. Contact= Measured value	Assessment
<i>Acetic acid 3 %</i>	<i>mg/dm²</i>	<i>10 %</i>	1.	< 1	< 1	< 1	<i>passed</i>
			2.	< 1	< 1	< 1	<i>passed</i>
			3.	< 1	< 1	< 1	<i>passed</i>
<i>Ethanol 10 %</i>	<i>mg/dm²</i>	<i>10 %</i>	1.	< 1	< 1	< 1	<i>passed</i>
			2.	< 1	< 1	< 1	<i>passed</i>
			3.	< 1	< 1	< 1	<i>passed</i>
<i>Olive oil</i>	<i>mg/dm²</i>	<i>30 %</i>	1.	< 1	< 1	< 1	<i>passed</i>
			2.	< 2	3.2	< 2	<i>passed</i>
			3.	< 1	< 1	< 1	<i>passed</i>
<i>Ethanol 95 %</i>	<i>mg/dm²</i>	<i>10 %</i>	1.	< 1	< 1	< 1	<i>passed</i>
			2.	< 1	< 1	< 1	<i>passed</i>
			3.	< 1	< 1	< 1	<i>passed</i>
<i>Isooctane</i>	<i>mg/dm²</i>	<i>10 %</i>	1.	< 1	< 1	< 1	<i>passed</i>
			2.	< 1	< 1	< 1	<i>passed</i>
			3.	< 1	< 1	< 1	<i>passed</i>

According to Article 12 of Regulation (EU) No. 10/2011 plastic materials and articles shall not transfer their constituents to food simulants in quantities exceeding 10 milligrams of total constituents released per dm² of food contact surface (mg/dm²). With regard to manner and extent of the performed overall migration test the limiting value is met by the present sample.

3.4. Specific migrations

3.4.1. Metals

Test conditions:

Type of Contact: *Insert*

Method: *DIN EN ISO 17294-2:2014-01*

Used Simulant: *Acetic Acid 3 %, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml*

Parameter	Limiting value^[5]:	Unit	1. Contact *	2. Contact *	3. Contact * = Measured value	Assessment:
<i>Aluminium^[5]</i>	≤ 1.0	<i>mg/kg</i>	< 0.1	< 0.1	< 0.1	<i>passed</i>
<i>Antimony^[8]</i>	≤ 0.04	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Arsenic^[8]</i>	≤ 0.01	<i>mg/kg</i>	< 0.002	< 0.002	< 0.002	<i>passed</i>
<i>Barium^[6]</i>	≤ 1.0	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Lead^[8]</i>	≤ 0.01	<i>mg/kg</i>	< 0.002	< 0.002	< 0.002	<i>passed</i>
<i>Cadmium^[8]</i>	≤ 0.002	<i>mg/kg</i>	< 0.001	< 0.001	< 0.001	<i>passed</i>
<i>Chromium^[8]</i>	≤ 0.01	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Cobalt^[6]</i>	≤ 0.05	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Iron^[6]</i>	≤ 48.0	<i>mg/kg</i>	< 0.1	< 0.1	< 0.1	<i>passed</i>
<i>Copper^[6]</i>	≤ 5.0	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Lithium^[6]</i>	≤ 0.6	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Manganese^[6]</i>	≤ 0.6	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Nickel^[7]</i>	≤ 0.02	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Mercury^[8]</i>	≤ 0.01	<i>mg/kg</i>	< 0.001	< 0.001	< 0.001	<i>passed</i>
<i>Zinc^[5]</i>	≤ 5.0	<i>mg/kg</i>	< 0.05	< 0.05	< 0.05	<i>passed</i>
<i>Europium^[8]</i>	≤ 0.05	<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Gadolinium^[8]</i>		<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Lanthan^[8]</i>		<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>
<i>Terbium^[8]</i>		<i>mg/kg</i>	< 0.01	< 0.01	< 0.01	<i>passed</i>

* relative measurement uncertainty 30 %

^[5] according to Regulation (EU) No 10/2011 adapted by Regulation (EU) 2016/1416 - OJ L 230, 25.8.2016, p. 22–42

^[6] according to Regulation (EU) No 10/2011 - OJ L 12, 15.1.2011, p. 1–89

^[7] according to Regulation (EU) No 10/2011 adapted by Regulation (EU) 2017/752 - OJ L 113, 29.4.2017, p. 18–23

^[8] according to Regulation (EU) No 10/2011 adapted by Regulation (EU) 2020/1245 - OJ L 288, 03.9.2020, S. 1–19

According to information provided by our raw material supplier no monomers or additives are used, which are controlled by a specific migration limit:

3.4.2. Antioxidants and phthalates

Test conditions:

Type of Contact: Insert

Method: WEX 2619

Used Simulant: Ethanol 95 %, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml

Parameter	Limiting value ^[a] :	Unit	1. Kontakt	2. Kontakt	3. Kontakt = Measured value	Assessment:
Di-n-butylphthalat (DBP) CAS No. 84-74-2	≤ 0.12 ; $\leq 0.6^{[b]}$; $\leq 60^{[a]}$	mg/kg	< 0.005	< 0.005	< 0.005	passed
Butylbenzylphthalat (BBP) CAS No. 85-68-7	≤ 6 ; $\leq 0.6^{[b]}$; $\leq 60^{[a]}$	mg/kg	< 0.01	< 0.01	< 0.01	passed
Di-2-ethylhexylphthalat (DEHP) CAS No. 117-81-7	≤ 0.6 ; $\leq 0.6^{[b]}$; $\leq 60^{[a]}$	mg/kg	< 0.01	< 0.01	< 0.01	passed
Diisononylphthalat (DINP) CAS No. 28553-12-0	$\leq 1.8^{[c]}$; $\leq 60^{[a]}$	mg/kg	< 0.01	< 0.01	< 0.01	passed
Diisodecylphthalat (DIDP) CAS No. 26761-40-0	$\leq 1.8^{[c]}$; $\leq 60^{[a]}$	mg/kg	< 0.01	< 0.01	< 0.01	passed
Sum of Diisononylphthalat (DINP) and Diisodecylphthalat (DIDP)	$\leq 1.8^{[c]}$; $\leq 60^{[a]}$	mg/kg	< 0.02	< 0.02	< 0.02	passed
Diisobutylphthalat (DIBP) CAS No. 84-69-5	$\leq 0.6^{[c][e]}$; $\leq 60^{[a][e]}$	mg/kg	< 0.005	< 0.005	< 0.005	passed
Sum (DBP), (DIBP), (BBP) and (DEHP), calculated as DEHP-Equivalents (DBP $\times$ 5 + DIBP $\times$ 4 + BBP $\times$ 0,1 + DEHP $\times$ 1)	$\leq 0.6^{[b]}$	mg/kg	< 0.056	< 0.056	< 0.056	passed

^[a] SML(T) No. 32

^[b] SML(T) No. 36

^[c] SML (T) No. 26

^[d] Must not be used together with DBP, BBP, DEHP and DIBP.

^[e] Diisobutyl phthalate, FCM No 1085, with synonyms 1,2- bis(2-methylpropyl) benzene1,2-dicarboxylate or 'DIBP' and CAS number 84-69-5 is not listed as an authorised substance in Table 1 of Annex 1 Regulation (EU) No 10/2011. However, it may co-occur with other phthalates as a consequence of its use as an aid to polymerisation and is included in group restrictions with the assignment FCM No 1085

3.4.3. Primary aromatic amines, calculated as aniline hydrochloride

Test conditions:

Type of Contact: Insert

Method: ASU L 00.00-6 (1995-01) + (2002-12)

Used Simulant: Acetic Acid 3 %, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml

Limiting value ^[6] : max.	Unit	1. Contact*	2. Contact*	3. Contact* = Measured value	Assessment:
< 0.01	mg/kg	< 0.002	< 0.002	< 0.002	passed

* relative Measurement uncertainty 35 %

3.4.4. Primary aromatic amines (single substances)

Test conditions:

Type of Contact: *Insert*

Method: *WBSE-98 (LC-MS/MS)*

Used Simulant: *Acetic Acid 3 %, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml*

Parameter	CAS	Limiting value ^[5]:	Unit	Measured value*:	Assessment:
Aniline ^[c]	62-53-3	10 ^[b]	µg/kg	< 0.1	passed
o-Toluidine ^[c]	95-53-4	2	µg/kg	< 0.1	passed
o-Anisidine ^[c]	90-04-0	2	µg/kg	< 0.1	passed
4-Chloroaniline ^[c]	106-47-8	2	µg/kg	< 0.1	passed
p-Cresidine ^[c]	120-71-8	2	µg/kg	< 0.1	passed
4-Chloro-o-toluidine ^[c]	95-69-25	2	µg/kg	< 0.1	passed
2-Methyl-5-nitroaniline ^[c]	99-55-8	2	µg/kg	< 0.25	passed
4-Aminodiphenyle ^[c]	92-67-1	2	µg/kg	< 0.1	passed
4,4'-Oxydianiline ^[c]	101-80-4	2	µg/kg	< 0.1	passed
3,3'-Dimethylbenzidine ^[c]	119-93-7	2	µg/kg	< 0.1	passed
4,4'-Thiodianiline ^[c]	139-65-1	2	µg/kg	< 0.1	passed
3,3'-Dimethyl-4,4'-diaminodiphenylmethane ^[c]	838-88-0	2	µg/kg	< 0.1	passed
4,4'-Methylen-bis-(2-chloroaniline) ^[c]	101-14-4	2	µg/kg	< 0.1	passed
p-Toluidine	106-49-0	10 ^[b]	µg/kg	< 0.25 ^[d]	passed
2,4-Toluyldiamine ^[c]	95-80-7	2	µg/kg	< 0.1	passed
2,4-Diaminoanisole ^[c]	615-05-4	2	µg/kg	< 0.1	passed
2-Naphthylamine ^[c]	91-59-8	2	µg/kg	< 0.1	passed
Benzidine ^[c]	92-87-5	2	µg/kg	< 0.1	passed
4,4'-Diaminodiphenylmethane ^[c]	101-77-9	2	µg/kg	< 0.1	passed
o-Aminoazotoluene ^[c]	97-56-3	2	µg/kg	< 0.1	passed
3,3'-Dimethoxybenzidine ^[c]	119-90-4	2	µg/kg	< 0.1	passed
3,3'-Dichlorobenzidine ^[c]	91-94-1	2	µg/kg	< 0.1	passed
2,4,5-Trimethylaniline ^[c]	137-17-7	2	µg/kg	< 0.1	passed
4-Aminoazobenzene ^[c]	60-09-3	2	µg/kg	< 0.1	passed

* Masured value = Mean value from triple determination

^[c] in Appendix 8 of Regulation (EC) No. 1907/2006

^[b] Limiting value of the sum

^[d] The LOQ of p-Toulidine had to be increased due to matrix effect.

3.4.5. Alkyl(C8-C22)sulfonic acids [FCM 16; Ref.-no. 34230]

Test conditions:

Type of Contact: *Insert*

Method: *WEX 656 (LC-MS/MS)*

Used simulant: *Ethanol 95 %, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml*

<i>Limiting value</i> ^[6] :	<i>Unit</i>	<i>1. Contact*</i>	<i>2. Contact*</i>	<i>3. Contact* = Measured value</i>	<i>Assessment:</i>
< 6,0	mg/kg	< 1,0	< 1,0	< 1,0	<i>passed</i>

3.4.6. N,N-Bis(2-hydroxyethyl)alkyl(C8-C18)amin [FCM 19; Ref.-no: 39090] and N,N-Bis(2-hydroxyethyl)alkyl(C8-C18)aminhydrochloride [FCM 20; Ref.-no: 39120]

Test conditions:

Type of Contact: *Insert*

Method: *WEX 1022*

Used Simulant: *Olive oil, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml*

<i>Limiting value</i> ^[5] :	<i>Unit</i>	<i>1. Contact*</i>	<i>2. Contact*</i>	<i>3. Contact*</i>	<i>Assessment:</i>
< 1.2*	mg/kg	< 1.0	< 1.0	< 1.0	<i>passed</i>

* SML(T) calculated as tertiary amine

3.4.7. Octadecyl-3-(3,5-di-ter-butyl-4-hydroxyphenyl)propionate [FCM 433; Ref.-no. 68320]

Test conditions:

Type of Contact: *Insert*

Method: *WBSE-89 (GC-MS)*

Used simulant: *Ethanol 95 %, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml*

<i>Limiting value</i> ^[6] :	<i>Unit</i>	<i>1. Contact*</i>	<i>2. Contact*</i>	<i>3. Contact* = Measured value</i>	<i>Assessment:</i>
< 6,0	mg/kg	< 1,0	< 1,0	< 1,0	<i>passed</i>

3.5. GC-MS-Overview analysis (NIAS[6]-Screening) according to the EPA Method 8270D:

Test conditions:

Type of Contact: *Insert*

Method: *EPA 8270D (GC-MS)*

Used Simulant: *Ethanol 95 %, for 10 d at 60 °C, with a S:V of 3.8 dm²:500 ml*

The migrate was analyzed gas chromatographically by means of mass spectrometric detection. For the identification of the signals in the chromatogram a commercial mass spectra library was used. Results are expressed in hexadecane (SVOCs) equivalents and may vary to the real amount. We point out that the mentioned amounts may vary to the real amounts as this is a screening approach.

Non-volatile substancen (SVOCs):		
Substance	CAS	Concentration[#] [mg/kg]
<i>Aliphatic hydrocarbons (C12-C16) (Sum) (1)</i>	-	0.21
<i>Aliphatic hydrocarbons (C16+) (Sum) (1)</i>	-	1.15
<i>Methyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate (4)** Metilox / Irganox 1300)</i>	6386-38-5	0.01
<i>Irgafos 168 (3)</i>	31570-04-4	0.33
<i>Oxidised Irgafos 168 (3)</i>	95906-11-9	0.23
<i>2,4-Di-tert-buthyl-phenol (3)(4)*</i>	96-76-4	0.03
<i>Not identified alcohol (2)</i>	-	0.03
<i>Not identified compounds containing aromatic ring (Sum)(2)</i>	-	0.02

[#] Measurement uncertainty 65% (the repeatability within a measurement series of a sample (same substance) < 10%)

* Cramer-Class I: Limiting value: (sTDI) of 0,03 mg/kg b.w./day resulting in a derived SML value of 1,8 mg/kg foodstuff

** Cramer-Class II: Limiting value: (sTDI) of 0,009 mg/kg b.w./day resulting in a derived SML value of 5,4 mg/kg foodstuff

Assessment of NIAS^[6] screening results

Aliphatic hydrocarbons (1)

Aliphatic hydrocarbons were detected during the investigation. Currently, no assessment values for the migration of hydrocarbons exist within the framework of Regulation (EU) 10/2011. As the sample at hand is made of polyolefin plastic, it is possible that the hydrocarbons originate from the plastic material itself.

Not identified compounds (2)

According to the type and scope of the investigations carried out, compounds that were not clearly identified were recorded. Since no clear identification is possible based on the mass spectrum, a final evaluation cannot be made at this point.

Irgafos 168, Oxidised Irgafos 168 (3) and 2,4-Di-tert-butylphenol (4)

According to the type and extent of the NVOC-GC-MS analysis carried out, the substances listed above were recorded. Oxidised Irgafos 168 and 2,4-Di-tert-butylphenol(5) may be degradation or reaction product of Irgafos 168. Irgafos 168 is used as an antioxidant in plastics production and is listed in Annex I of Regulation (EU) No 10/2011 without restriction. The risk assessment of these substances should cover the substance itself, relevant impurities and reaction and degradation products foreseeable in the intended use. From this point of view, the concentration in the migrate of the present sample is judged to be unremarkable.

^[6] according to Regulation (EU) No 10/2011 - OJ L 12, 15.1.2011, p. 1–89

Other substances (4)

According to the type and scope of the investigation carried out, further substances were detected that are not listed in Annex I of Regulation (EU) No. 10/2011, i.e. here the guideline value for non-listed substances of < 0.01 mg/kg (not detectable) should be leading the way within the meaning of this Regulation. In addition, Article 19 of Regulation (EU) No 10/2011 forces, that substances that have been detected and are not included in Annex I to the Union list must be subject to a risk assessment in accordance with scientifically accepted standards.

Migration limits for the detected substances do not exist at present, toxicological studies on these substances are also not available to us. We are therefore guided by the classification of substances into Cramer classes based on structural properties. This was done according to the "Threshold of Toxicological Concern" (TTC) concept using the software "Toxtree 3.1.0, Revised Cramer Decision Tree".

The underlying structure of Phenol, 2,4-bis(1,1-dimethylethyl)-, leads to a classification of Cramer Class I, for which an intake of up to 30 µg/kg body weight/day is considered tolerable. Assuming a person weighing 60 kg, this corresponds to a permitted limiting value of 1.8 mg substance/person per day.

The underlying structure of Methyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate leads to a classification of Cramer Class II, for which an intake of up to 9.0 µg/kg body weight/day is considered tolerable. Assuming a person weighing 60 kg, this corresponds to a permitted limiting value of 540 µg substance/person per day.

Considering all substances, for which a classification into a Cramer class is given, considering the different hazard classes, a daily consumption of 1 kg of food, that has been in contact with the article under similar conditions and has comparable dissolving properties with regard to the substances, will not exceed the limiting values and therefore the content of the other detected substances can be regarded as inconspicuous.

4. Reference to „Dual-Use-Substances“:

The raw material contains substances also authorised as direct food additives ("Dual use additives") according to Regulation (EG) No 1333/2008^[10] in its actual version.

FCM 009; Ref.-no. 30610 - Lubricant: Calciumstearate (E470a)

FCM 053; Ref.-no. 56585 - Emulsifier: Ester of Glycerol with Stearic acid: (E471)

FCM 575; Ref.-no. 76721 - Lubricant: Polydimethylsiloxan (MG > 6800 Da)

FCM 610; Ref.-no. 93440 - Pigment: TiO₂ (E171)

No functional barrier of plastic material is used.

To ensure the traceability of the product according to Regulation (EC) No 1935/2004 a date-stamp is used at the product itself or a LOT No. is printed on the product label.

In addition, we have to point out that the used raw material is not intended to be used for medical, pharmaceutical or healthcare applications and the manufacturer do not support their use for such applications. This product is neither tested nor represented as suitable for medical or pharmaceutical uses by us. It is in the scope of the end-user to validate the product for applications which differs from the guidelines of the Commission Regulation (EU) No 10/2011.

VITLAB GmbH

Grossostheim, 11 February 2025

Wolfgang Nicolaus

Geschäftsführer
Managing Director

i.A. Dr. Stephan Schmidt

Beauftragter Product Compliance
Regulatory Affairs

This letter has been typed and is valid without signature.

^[10] according to Regulation (EU) No 1333/2008 - OJ L 354, 31.12.2008, p. 16–33